

CORFLON

Value for Money **PTFE** system - **water based**

- Easy to use
- Well balanced abrasion resistance and non-stick properties
- Good corrosion resistance
- Choice of primers with different reinforcement level
- PTFE system, water based

We're sure to have the right solution for your application; contact us to learn more.



Characteristic

Number of Layer	2
Coating Thickness μm	20-25
Curing Temperature $^{\circ}\text{C}$	420
Service Temperature $^{\circ}\text{C}$	250

Substrates

Substrate	Pretreatment	Suitability
alu	degrease & sandblasting with corundum	✓✓
Carbon steel	degrease & sandblasting with corundum	✓✓

Testing Methods

Basic Properties

- Suitability for Food Contact
- Visual Aspects
- Dry Film Thickness (DFT)
- Adhesion (Cross hatch)